



ООО «Полимер Экспорт»

ПРОМЫШЛЕННЫЕ ЛАКОКРАСОЧНЫЕ ПОКРЫТИЯ

8 (4932)773-503



raum-profile.ru
inmarketing@gk-rp.ru



Release date: 01.10.2024
Manufacturer: Russian Federation
TY 20.30.22-008-69372620-2021

Primer Polytex BS

CERTIFICATE

Certificate of conformity to requirement documents № ПОСС RU Д-РУ.PA02.B.12416/21 from 23.12.2021.
Safety data sheet of chemical products from 28.01.2022.
MSDS №69372620.20.85257 от 14.11.2023 г.

DESCRIPTION

Two component polyurethane primer, hardened by aliphatic polyisocyanate.

FIELDS OF APPLICATION

Polytex BS primer enhances the protective anti-corrosion properties of the complex coating. It is intended to prime metal structures in the industrial atmosphere of moderate-cold and cold climates exposed to vibration stress.

It is used to prime railway and urban transport, construction metal structures, oil and gas pipelines, tanks, oil storage facilities, bridges, hydraulic facilities, power transmission towers, cell towers, devices and equipment, as well as other metal surfaces with high requirements for hardness, strength, abrasion resistance, moisture resistance. It is characterized by good sanding, bending strength, improved adhesion, and accelerated open time. As part of a complex coating, it is successfully used in moderate and cold climates, while providing long-term protection against corrosion.

Information on the material resistance to various media is available on request.

Main fields of application: oil and gas industry, transport construction, power engineering, tank equipment, mechanical engineering, chemical industry.

TECHNICAL DATA

Color	Grey, white, reddish-brown, light mustard (other colours due to customer need)	
Mass fraction of dry residue component A	60-72% (depending on colour and gloss grade)	
Adhesion to metal (GOST 15140), no more	1 point	
Density component A	1,35±0,05 g/cm ³	
Density components A+B	1,34±0,05 g/cm ³	
Max. one layer thickness, viscosity 100 s	500 microns wet layer	
Dry volume residue	50±5%	
Dry film thickness and estimated consumption	Dry film thickness, microns	Estimated consumption, g/m ²
min	40	97
max	250	609
Hardener	Polytex ST Polytex ST2 Polytex ST2S	

Due to the wide range in color and / or gloss, this description is informative.

Certificate of quality is the document confirming the quality of each production lot.

INSTRUCTION FOR USE

Metal surface should be abrasive blasted to grade 1 or 2 to GOST 9.402 (Sa 2,5 or Sa 2 to ISO8501-1:2007). Clean surface must be free from dust and grease.
If the quality of surface preparation decreases, the service life and its operating performance may change.

CONDITIONS

Ambient temperature from +5°C to +30°C.
Relative air humidity no more 80%.



APPLICATION

Blending	Polyurethane primer consists of two components: component A - basis, component B - hardener. Before use, pre-mix component A with a low-speed drill with mixing nozzle, then mix with component B in stoichiometric ratio in the delivery form. Mix the resulting material thoroughly until smooth. After the hardener is added into the semi-finished product, the material should be allowed to stand for at least 5-10 minutes.
Proportions	Polytex ST hardener 100:10 by weight 8:1 by volume Polytex ST2 hardener 100:9 by weight 9,5:1 by volume Polytex ST2S hardener 100:22 by weight 3:1 by volume
Pot life at 20 ±2°C, no less	3 hours
Air-free spraying	Thinning: 5-30% Nozzle diameter: 0,011-0,017" Initial pressure: 120-160 atm
Air spraying	Operational viscosity: 25-100 s Thinning: 5-35% Nozzle diameter: 1,8-2,5 mm Initial pressure: 3,0-4,0 atm
Brush, roller	Can be recommended for small and hard-to-reach areas. Thin the primer-enamel depending on the working conditions when using brush.
Thinner	Formula thinner Polytex, RP-1K.
Cleaner	Formula thinner Polytex, RP-1K, RP-1K F, thinners of type P4, P5.
Finishing	Tubing, pistol and other spraying tools must be cleaned after using.
Cleaning	Clean straight after using due to painting equipment manual.

DRYING TIME

Surface temperature	+5°C	+10°C	+20°C	+30°C	+40°C
Degree 1 (GOST 19007)	4,5 h	2,5 h	1 h	45 min	30 min
Degree 3 (GOST 19007)	7 h	5 h	2 h	1 h	50 min
Minimum recoating interval	7 h	4 h	1 h	30 min	30 min
Start of operation	14 d	10 d	7 d	7 d	7 d

Minimum recoating interval: the minimum recommended time the next coat to be applied.

Start of operation: the minimum time the coating to be exposed to a given environment.

These data should be considered only as indicative for a wet film thickness of 100 microns.

PACKAGE SIZE

Metal euro bucket 21 l: basis 20kg;
 Metal bottle 3 l: hardener 2,0 kg (Polytex ST hardener)

Metal euro bucket 21 l: basis 20kg;
 Metal bottle 3 l: hardener 1,8 kg (Polytex ST2 hardener)

Metal euro bucket 21 l: basis 20kg;
 Metal bottle 5,2 l: hardener 4,4 kg (Polytex ST2S hardener)



ООО «Полимер Экспорт»

ПРОМЫШЛЕННЫЕ ЛАКОКРАСОЧНЫЕ ПОКРЫТИЯ

8 (4932)773-503

raum-profile.ru
lnmarketing@gk-rp.ru



STORAGE

Store in a tightly closed container in a closed dry room at a temperature from - 40 ° C to + 40 ° C, away from sources of ignition, protecting from mechanical damage, direct sunlight and moisture.

GUARANTEED STORAGE LIFE

Expire date is 12 months in case if delivery and storing rules are followed. After expire date shouldn't be used without tests.

HEALTH AND SAFETY

When painting work, use personal protective equipment (respirators, gloves, glasses, etc.). Work inside the room should be carried out with artificial (local, general) or natural ventilation. Use the primer only in places without sources of open fire and ignition. Avoid contact with skin or eyes. In case of skin contact immediately wipe with a rag or cotton swab, rinse thoroughly with soapy water, do not use solvents. In case of eyes contact rinse with clean water for at least 10 minutes, consult a doctor. In case of ingestion, consult a doctor.

RECYCLING

Packing materials are recycled as consumer waste

Further Information.



Собственное
современное
производство



Система
Менеджмента
Качества
(ISO 9001)



Аттестованная
лаборатория



На рынке
с 2002 года



ООО «Полимер Экспорт»

ПРОМЫШЛЕННЫЕ ЛАКОКРАСОЧНЫЕ ПОКРЫТИЯ

 **8 (4932)773-503**

 **raum-profile.ru**
lnmarketing@gk-rp.ru

The recommendations above are based on our own research and our best knowledge but don't fully guarantee any particular case as it depends on the quality, friability and porosity of the base. The local working conditions and methods may vary and are beyond our control. Therefore we cannot be held responsible for the actual work on the site.
The information is currently updating..



Собственное
современное
производство



Система
Менеджмента
Качества
(ISO 9001)



Аттестованная
лаборатория



На рынке
с 2002 года