

Release date: 01.08.2025.
Manufacturer: Russian Federation
TY20.30.22-007-69372620-2021

Primer-enamel ALURON AT HQ

CERTIFICATE

State Registration Certificate № RU.8 RU.8.08.09.008.E.000072.12.21 from 27.12.2021.
Declaration of Conformity № РОСС RU Д-RU.PA01.B.16540/25 from 27.05.2025
MSD №69372620.20.51163 from 14.08.2025

DESCRIPTION

Single component anticorrosion primer-enamel (DTM). No need to prime the surface.

FIELDS OF APPLICATION

ALURON AT paint-enamel is used to paint metal surfaces in the reduced drying mode, including assembly painting. Primer-enamel can be applied at subzero temperatures.

It is used for anti-corrosion protection and repair painting of internal and external surfaces of vehicles (agricultural machinery, construction equipment, public transport, railway transport), machine parts and mechanisms, construction metal structures surfaces, containers, hangars, roofs as well as other metal products exposed to increased mechanical and atmospheric effects. ALURON AT HQ primer-enamel is used as repair coating as well as finishing products after assembly both indoor and outdoor.

Information on the material resistance to various media is available on request.

Main fields of application: powery engineering, mechanical engineering, railway transport facilities, transport construction.

TECHNICAL DATA

Colour	Colour list of RAL	
Gloss	G035: 0-35 points.	
Mass fraction of dry residue	60% (depending on colour and gloss grade) 1	
Adhesion to metal (GOST 15140), no more	1 point	
Density	1,3 - 1,6 g/cm ³	
Max. one layer thickness without thinning	200 microns wet layer	
Max. one layer thickness, viscosity 25 s	200 microns wet layer (thinner RP-1KF)	
Dry volume residue	50±7 %	
Dry film thickness and estimated consumption	Dry film thickness, microns	Estimated consumption, g/m ²
min	60	174
max	120	348
Open time to grade 3 at 20 ±2°C, no more (wet film thickness 100 microns)	60 min	
Open time to grade 3 at -5°C, no more (wet film thickness 100 microns)	120 min	
Readiness for operation	7 days	

INSTRUCTION FOR USE

Due to the wide range in color and / or gloss, this description is informative.
Certificate of quality is the document confirming the quality of each production lot.



Metal surface should be abrasive blasted to grade Sa 2,5 or Sa 2 to GOST R ISO 8501-1-2014. Clean surface must be free from dust and grease.

If the quality of surface preparation decreases, the service life and its operating performance may change.

CONDITIONS

Basis temperature higher than dew point no less than 3°C.
Ambient temperature from +5°C to +35°C.
Relative air humidity no more 80%.

APPLICATION

Preparing	Ready to use. Stir thoroughly before use with mixer. Thin if needed with formula thinner RP-1K, RP-1K F
Air-free spraying	Thinning: 0-10% Nozzle diameter: 0,011-0,017" Initial pressure: 120-160 atm
Air spraying	Operational viscosity: 25-60 s Thinning: 10-30% Nozzle diameter: 1,8-2,5 mm Initial pressure: 3,0-4,0 atm
Cross linking at 20°C	No less 15 min
Brush, roller	Can be recommended for small and hard-to-reach areas. Thin the primer-enamel depending on the working conditions when using brush.
Thinner	Formula thinner RP-1K, RP-1K F
Cleaner	Formula thinner RP-1K, RP-1K F, thinners of types P4, P5.
Closing-down	Tubing, pistol and other spraying tools must be cleaned after using
Cleaning	Wash the tools after using immediately. The frequency of washing depends on the amount of sprayed material, the temperature and the time since the shutdown, including any time lag.

PACKAGE SIZE

Metal euro bucket 21 l: 20 kg

STORAGE

The material packed in a metal eurobucket with a volume of 21 liters should be stored in a tightly closed container in a closed dry room at a temperature from - 40 ° C to + 40 ° C, away from sources of ignition, protecting from mechanical damage, direct sunlight and moisture.

GUARANTEED STORAGE LIFE

ALURON AT HQ primer enamel guaranteed shelf life is 12 months from the date of manufacture, subject to the consumer's compliance with the rules of transportation and storage.

HEALTH AND SAFETY

When painting work, use personal protective equipment (respirators, gloves, glasses, etc.). Work inside the room should be carried out with artificial (local, general) or natural ventilation. Use the primer-enamel only in places without sources of open fire and ignition. Avoid contact with skin or eyes. In case of skin contact immediately wipe with a rag or cotton swab, rinse thoroughly with soapy water, do not use solvents. In case of eyes contact rinse with clean water for at least 10 minutes, consult a doctor. In case of ingestion, consult a doctor. Pressurized aerosol can: explosion is possible when heated. Do not spray near sources of open fire and incandescent objects. Do not smoke during use.



ООО «Полимер Экспорт»

ПРОМЫШЛЕННЫЕ ЛАКОКРАСОЧНЫЕ ПОКРЫТИЯ

 **8 (4932)773-503**

 **raum-profile.ru**
lnmarketing@gk-rp.ru



RECYCLING

21 liters metal eurobucket should be disposed of as household waste.

Further Information.

The recommendations above are based on our own research and our best knowledge but don't fully guarantee any particular case as it depends on the quality, friability and porosity of the base. The local working conditions and methods may vary and are beyond our control. Therefore we cannot be held responsible for the actual work on the site. The information is currently updating.



Собственное
современное
производство



Система
Менеджмента
Качества
(ISO 9001)



Аттестованная
лаборатория



На рынке
с 2002 года